Concrete Deck repair and waterproof Wilkerson House

Panama City Beach, Fl



- Beaches Construction Company
- PO Box 18155
- Panama City Beach, Fl 32417
- 850-235-4811

WWW.beachesconstruction.com

After Power wash of deck, exposing all cracks and damaged areas



Chipping all damaged and spalled concrete from rebar



Exposing rusted rebar



Removed all concrete around rebar including underneath by ¾" – cleaning off all rust and priming rebar with inorganic zinc



Removed all concrete around rebar including underneath by ¾" – cleaning off all rust and priming rebar with inorganic zinc



Removed all concrete around rebar including underneath by ¾" – cleaning off all rust and priming rebar with inorganic zinc



Pour new 5000 PSI concrete over repair area and level



Pour new 5000 PSI concrete over repair area and level



Pour new 5000 PSI concrete over repair area and level



"V" groove all cracks and fill with epoxy and sand mix to seal crack



"V" groove all cracks and fill with epoxy and sand mix to seal crack



Applying base coat of Vulkum waterproof membrane over repaired concrete



Applying base coat of Vulkum waterproof membrane over repaired concrete



Applying Top coat of Vulkum waterproof membrane over repaired concrete with sand broadcast for non slip surface



Finished deck with a non slip surface and waterproofed to protect the concrete deck for many years



Another successful project by



Beaches Construction Company

7703 McElvey road #D

Panama City Beach, Fl. 32408

850-235-4811 office phone

850-230-3617 office fax

www.beachesconstruction.com